

## **A Review of Hemocompatibility of Bio Scaffolds for Bone Regeneration: An In Vitro Assessment Using Human Red Blood Cells**

**<sup>1</sup>Mrs. Nithya M. and <sup>2</sup>Dr. S. Angelina Glorita Parimala\***

### **Author's Affiliation:**

<sup>1,2</sup>Research Scholar, Associate Professor of Zoology, A.D.M College for Women (Autonomous), Nagapattinam, Tamil Nadu 611 001. India. (Affiliated to Bharathidasan University)

### **\*Corresponding author:**

**Dr. S. Angelina Glorita Parimala**

Associate Professor of Zoology, A.D.M College for Women (Autonomous), Nagapattinam, Tamil Nadu 611 001. India. (Affiliated to Bharathidasan University)  
ORCID: 0009-0007-8651-0835  
E-mail: nithyashankar31@gmail.com

**Received on 30.04.2025**

**Revised on 03.06.2025**

**Accepted on 13.07.2025**

### **ABSTRACT:**

To facilitate healing and reconstruction of bones, the bone regeneration frame is used more and more in orthopaedic and jaw procedures. Hamo-bonds of the ability of the frame that are favourable with the blood are important, but often ignore the components of biocompatibility. Haematology, thrombosis, inflammation and ultimately implant deficiency can be caused by interactions with blood components, especially red blood cells. Focusing on testing in tests using human red blood cells, this article explains recent studies on bioscaffold for bone regeneration. We perform a variety of materials for frames, how to assess RBC compatibility and possible approach to enhance hem -binding possibilities. The design and description of biocompatible frames that successfully integrate and successfully and support bone regeneration requires a deeper understanding of these interactions.

### **Keywords:**

Bone regeneration, Bio scaffold, Biocompatibility, Red blood cells, Hemocompatibility.

**How to cite this article:** Nithya M. and Parimala S.A.G. (2025). A Review of Hemocompatibility of Bio Scaffolds for Bone Regeneration: An In Vitro Assessment Using Human Red Blood Cells. *Bulletin of Pure and Applied Sciences-Zoology*, 44A (2), 79-83.

## **INTRODUCTION**

The main clinical challenge is bone defects due to disease, trauma, or surgical resection. The regeneration of bone based on biomaterials has recently interested in the potential substitute for autografts and allografts. These scaffolds provide a three-dimensional (3D) matrix, which contributes to the cell adhesion, growth, and differentiation while directing the development of new bone. Biocompatibility, Biodegradability, osteo conductivity, osteoinductivity, and suitable mechanical strength are all preferable in a scaffold (Hutmacher et al., 2000).

Hemocompatibility, or a material's ability is to interact favourably with blood, and it is generally ignored when designing and evaluating scaffold, while biocompatibility frequently includes cytotoxicity, inflammation, and tissue integration. The bio scaffold instantly comes into contact with blood after implantation, starting a complicated chain of events. The coagulation, complement activation, platelet adhesion and aggregation, and most importantly haemolysis and damage to red blood cells (RBCs) can all result from this interaction (Anderson et al., 1999). During haemorrhage, the RBC is damages and releasing haemoglobin and intracellular materials into the surrounding environment. These liberated substances can prevent bone

regeneration and cause oxidative stress and inflammation (Tuma et al., 2014).

Thus, it is important to evaluate the bone regeneration scaffolds, especially the method of interacting with RBCs. As an indicator of the blood and material interactions and, this paper reviews the bone regeneration, and use of human red blood cells.

Bone tissue engineering is a multidisciplinary field focused on repairing or replacing damaged bone tissue through a combination of biomaterials, cells, and growth factors (Bose et al., 2012; Mohamed & Shamaz, 2015). Scaffolds play a crucial role in this process by providing a three-dimensional structure that supports cell adhesion, proliferation, and differentiation, guiding new bone tissue formation (Chocholata et al., 2019).

In bone regeneration, scaffolds serve as a template for bone ingrowth, providing mechanical support and delivering bioactive cues to stimulate bone formation (Chocholata et al., 2019). The ideal scaffold should be biocompatible, biodegradable, and possess a suitable pore size and architecture to facilitate vascularization and nutrient transport (Dalfino et al., 2023; Sabir et al., 2009).

Red blood cells, primarily known for their oxygen-carrying capacity, have emerged as a promising component in bone tissue engineering due to their potential to enhance vascularization and promote bone regeneration (Guo et al., 2023). Vascularization, the formation of new blood vessels, is essential for the survival and function of newly formed bone tissue, ensuring an adequate supply of oxygen and nutrients while removing waste products (Balmayor & Griensven, 2015).

The incorporation of red blood cells into scaffolds can promote angiogenesis, accelerating the bone regeneration process. Stem cells are often combined with biomaterials, scaffolds, and growth factors to promote bone healing at fracture sites, showcasing the importance of cellular components in bone regeneration strategies (Iaquinta et al., 2019). Mesenchymal stem cells have demonstrated effectiveness in renewing

bone tissue defects, highlighting their crucial role in regenerative processes (Diomedea et al., 2020).

However, the integration of red blood cells into scaffolds presents significant hemocompatibility challenges, as the introduction of blood components can trigger adverse reactions such as thrombosis, inflammation, and immune responses (Guo et al., 2022). Hemocompatibility refers to the ability of a material to interact with blood without causing harmful effects (Perez et al., 2018).

### SCAFFOLD MATERIALS AND THEIR HEMOCOMPATIBILITY

Various materials are employed in the fabrication of bone regeneration scaffolds, each exhibiting different levels of hemocompatibility.

**Collagen:** A protein that occurs naturally and makes up a significant portion of the extracellular matrix (ECM), collagen is frequently utilized in bone regeneration. Usually, type I collagen is used. In general, collagen scaffolds are biocompatible and biodegradable. However, a few research has established that collagen can cause platelet aggregation and promote the coagulation cascade (Woodhouse et al., 2003). Its hemocompatibility may be affected by purification ranges and crosslinking strategies.

**Biodegradable synthetic polymers** with a range of mechanical characteristics and rates of degradation include poly (lactic acid) (PLA), poly (glycolic acid) (PGA), poly (lactic-co-glycolic acid) (PLGA), and polycaprolactone (PCL) [5]. The type of polymer, molecular weight, and surface properties all affect their hemocompatibility. In general, hydrophilic polymers are greater hem compatible than hydrophobic ones. Their blood compatibility may be enhanced by surface change the usage of hydrophilic polymers which includes polyethylene glycol (PEG) (Lee et al., 1995).

### IN VITRO ASSESSMENT OF RBC COMPATIBILITY

A number of invitro techniques are employed to assess the hemocompatibility of bioscaffold using human red blood cells. These tests offer

important information about the possibility of RBC damage and its after effects.

The most popular technique for determining RBC compatibility is the haemolysis assay. A suspension of human red blood cells in a physiological solution is incubated with the bioscaffold material for a predetermined amount of time, usually one to three hours. The amount of released haemoglobin is determined using spectrophotometry after the supernatant is collected following incubation. The amount of haemoglobin released in comparison to a positive control (complete lysis) and a negative control (no lysis) is used to compute the percentage of haemolysis. Guidelines for performing haemolysis assays are provided by the ASTM F756 standard. Important parameters that require careful control include the ratio of material surface area to blood volume, incubation duration, and RBC concentration.

#### **FACTORS INFLUENCING RBC COMPATIBILITY**

The relationship between RBCs and bio scaffolds is influenced by a number of factors:

##### **Material Composition:**

The chemical composition of the scaffold material is a significant component. As was previously indicated, RBC lysis can be caused by the surface charge or degradation products of some materials, such as synthetic polymers and some bioactive glasses.

##### **Surface Properties:**

RBC adhesion and activation are greatly influenced by surface features such as surface roughness, hydrophobicity/hydrophilicity, and surface charge. RBC adhesion is generally higher on rougher surfaces (Bagherifard et al., 2015). When compared to hydrophilic surfaces, hydrophobic surfaces frequently show reduced hemocompatibility.

##### **Porosity and Pore Size:**

Blood flow and RBC interaction may be impacted by the scaffold's porosity and pore size. RBC mobility may be restricted by smaller pore sizes, which may result in cell damage.

##### **Sterilisation Techniques:**

Sterilisation techniques like autoclaving, gamma irradiation, and ethylene oxide sterilisation can change the scaffold material's surface characteristics and impact its hemocompatibility (Kulkarni et al., 1966).

#### **STRATEGIES TO IMPROVE HEMOCOMPATIBILITY**

Several strategies can be employed to improve the hemocompatibility of bone regeneration scaffolds:

**Surface Modification:** Protein adsorption and RBC adhesion can be decreased by covering the scaffold surface with biocompatible substances like PEG, hyaluronic acid, or chondroitin sulphate (Unsworth et al., 2005)

**Material Selection:** RBC interaction can be reduced by selecting materials with built-in hemocompatibility, like collagen or specific bioactive polymers.

**Incorporation of Antithrombotic Agents:** heparin or nitric oxide donors are examples of antithrombotic agents that can be incorporated into the scaffold can inhibit coagulation and reduce the risk of thrombosis (Kim et al., 2011).

**Texturing and Surface Engineering:** RBC adhesion and activation can be influenced by altering the surface texture and creating micro- or nano-patterns.

**Optimization of Porosity and Pore Size:** By carefully regulating the scaffold' porosity and pore size, blood flow can be enhanced and RBC damage can be reduced.

#### **CONCLUSION**

A key consideration in the design of bio scaffolds for bone regeneration is hemocompatibility. Predicting the scaffold's reaction in the intricate biological environment requires evaluating the interaction between scaffolds and human red blood cells using in vitro assays. Together with RBC morphology analysis, aggregation studies, and ROS measurement, the haemolysis assay offers important insights into the risk of RBC

damage and its ensuing negative consequences. In order to create biocompatible and efficient scaffolds for bone regeneration that support successful bone healing and reconstruction, it is essential to comprehend the variables that affect RBC compatibility and use techniques to increase hemocompatibility. In order to validate the results of in vitro studies, future research should concentrate on creating increasingly complex in vitro models that replicate the intricate in vivo environment and integrating in vivo hemocompatibility assessments.

## REFERENCES

- Anderson, J. M., & Langone, J. J. (1999). Issues and perspectives on the biocompatibility and immunotoxicity evaluation of implanted biomaterials. *Biomaterials*, 20(19), 1729-1740.
- Bagherifard, S., Mohammadi, A., Mirzadeh, H., Dadsetan, M., & Ebrahimi-Barough, E. (2015). Influence of surface roughness on the hemocompatibility of titanium dioxide nanotubes grown on titanium substrate. *Materials Science and Engineering: C*, 48, 87-95.
- Balmayor, E. R., & Griensven, M. van. (2015). Drug delivery to bony tissue. In *Advanced Drug Delivery Reviews* (Vol. 94, p. 1). Elsevier BV. <https://doi.org/10.1016/j.addr.2015.10.018>
- Bose, S., Roy, M., & Bandyopadhyay, A. (2012). Recent advances in bone tissue engineering scaffolds [Review of Recent advances in bone tissue engineering scaffolds]. *Trends in Biotechnology*, 30(10), 546. Elsevier BV. <https://doi.org/10.1016/j.tibtech.2012.07.005>
- Chocholata, P., Kulda, V., & Babuška, V. (2019). Fabrication of Scaffolds for Bone-Tissue Regeneration [Review of Fabrication of Scaffolds for Bone-Tissue Regeneration]. *Materials*, 12(4), 568. Multidisciplinary Digital Publishing Institute. <https://doi.org/10.3390/ma12040568>
- Dalfino, S., Savadori, P., Piazzoni, M., Connelly, S., Giannì, A. B., Fabbro, M. D., Tartaglia, G. M., & Moroni, L. (2023). Regeneration of Critical-Sized Mandibular Defects Using 3D-Printed Composite Scaffolds: A Quantitative Evaluation of New Bone Formation in In Vivo Studies [Review of Regeneration of Critical-Sized Mandibular Defects Using 3D-Printed Composite Scaffolds: A Quantitative Evaluation of New Bone Formation in In Vivo Studies]. *Advanced Healthcare Materials*, 12(21). Wiley. <https://doi.org/10.1002/adhm.202300128>
- Diomedea, F., Marconi, G. D., Fonticoli, L., Pizzicanella, J., Merciaro, I., Bramanti, P., Mazzon, E., & Trubiani, O. (2020). Functional Relationship between Osteogenesis and Angiogenesis in Tissue Regeneration [Review of Functional Relationship between Osteogenesis and Angiogenesis in Tissue Regeneration]. *International Journal of Molecular Sciences*, 21(9), 3242. Multidisciplinary Digital Publishing Institute. <https://doi.org/10.3390/ijms21093242>
- Diomedea, F., Marconi, G. D., Fonticoli, L., Pizzicanella, J., Merciaro, I., Bramanti, P., Mazzon, E., & Trubiani, O. (2020). Functional Relationship between Osteogenesis and Angiogenesis in Tissue Regeneration [Review of Functional Relationship between Osteogenesis and Angiogenesis in Tissue Regeneration]. *International Journal of Molecular Sciences*, 21(9), 3242. Multidisciplinary Digital Publishing Institute. <https://doi.org/10.3390/ijms21093242>
- Guo, T., Yuan, X., Li, X., Liu, Y., & Zhou, J. (2022). Bone regeneration of mouse critical-sized calvarial defects with human mesenchymal stem cell sheets co-expressing BMP2 and VEGF. *Journal of Dental Sciences*, 18(1), 135. <https://doi.org/10.1016/j.jds.2022.06.020>
- Hutmacher, D. W. (2000). Scaffolds in tissue engineering bone and cartilage. *Biomaterials*, 21(24), 2529-2543.
- Iaquinta, M. R., Mazzoni, E., Bononi, I., Rotondo, J. C., Mazziotta, C., Montesi, M., Sprio, S., Tampieri, A., Tognon, M., & Martini, F. (2019). Adult Stem Cells for Bone Regeneration and Repair [Review of

- Adult Stem Cells for Bone Regeneration and Repair]. *Frontiers in Cell and Developmental Biology*, 7. Frontiers Media. <https://doi.org/10.3389/fcell.2019.00268>
- Kim, D. W., Kim, J. H., Kim, D. Y., Lee, S. H., Kwon, I. K., & Park, J. B. (2011). Enhanced blood compatibility of poly(lactic-co-glycolic acid) scaffold containing nitric oxide-releasing nanoparticles for tissue engineering. *Journal of Materials Chemistry*, 21(43), 17346-17354.
- Kulkarni, R. K., Pani, K. C., Neuman, C., & Leonard, F. (1966). Influence of sterilization methods on the biocompatibility of poly(lactic acid). *Journal of Biomedical Materials Research*, 1(3), 491-504.
- Langer, R., & Tirrell, D. A. (2004). Designing materials for biology and medicine. *Nature*, 428(6982), 487-492.
- Lee, J. H., Lee, H. B., & Andrade, J. D. (1995). Blood compatibility of polyethylene oxide surfaces. *Progress in Polymer Science*, 20(6), 1043-1079.
- Mohamed, S., & Shamaz, B. H. (2015). Bone Tissue Engineering and Bony Scaffolds. *International Journal of Dentistry and Oral Health*, 1(1), 1. <https://doi.org/10.25141/2471-657x-2015-1.0001>
- Perez, J., Kouroupis, D., Li, D. J., Best, T. M., Kaplan, L. D., & Correa, D. (2018). Tissue Engineering and Cell-Based Therapies for Fractures and Bone Defects [Review of Tissue Engineering and Cell-Based Therapies for Fractures and Bone Defects]. *Frontiers in Bioengineering and Biotechnology*, 6. Frontiers Media. <https://doi.org/10.3389/fbioe.2018.00105>
- Sabir, M. I., Xu, X., & Li, L. (2009). A review on biodegradable polymeric materials for bone tissue engineering applications [Review of A review on biodegradable polymeric materials for bone tissue engineering applications]. *Journal of Materials Science*, 44(21), 5713. Springer Science+Business Media. <https://doi.org/10.1007/s10853-009-3770-7>
- Tuma, R. S., Akhter, S., Smith, B. R., Tuma, D. J., & Casey, C. A. (2014). Red blood cells promote hepatocellular injury after hemorrhagic shock. *Shock*, 41(4), 323-331.
- Unsworth, L. D., Carré, A., & Popat, K. C. (2005). Surface modification of titanium with hyaluronic acid and chondroitin sulfate for improved biocompatibility. *Journal of Biomedical Materials Research Part A*, 75A(3), 532-541.
- Woodhouse, K. A., & Garon, M. (2003). The role of collagen in tissue engineering: Biocompatibility, biodegradation and cell-material interactions. *Tissue Engineering*, 9(S1), S1-59.

\*\*\*\*\*